

5 % CALCIUM OCTOATE

TECHNICAL DATA SHEET

DESCRIPTION: Individually Calcium as little role in drying but can work effectively as “Auxiliary” drier when used in combination with other active driers. Calcium is often used to replace Lead where toxicity level matters in application like try Enamels, Baby Furniture finishes and Sanitary finishes. It is produced in different Calcium metal concentrations as 10%, 5% and 3%. It is a strong oxidizing catalyst for drying oils. It is most active surface drier.

SPECIFICATIONS: Calcium Octoate 10 %

SR.No	PARAMETERS	STANDARD RANGE
1	Appearance	Pale Yellow
2	Clarity	Clear.
3	Metal Content %	5 % ± 0.2%
4	Non Volatile At 120°C/1Hr	52 % ± 5 %
5	Specific Gravity @30° C	1.03 ±0.03
6	Water %	< 1.0% by KF method



Plot No. K-216, MIDC Waluj, Aurangabad - 431136. (Maharashtra) INDIA
Tel / Fax : +91-0240-2554727, Tel. : +91 - 7030416426
Email : rupesh@bhagwatiallied.com | bhagwatiallied@gmail.com
Website : www.bhagwatiallied.com

APPLICATIONS:

1. Drier for solvent based coatings
2. Driers for printing inks

PACKAGING: 25 kgs PE Pail and 200 kgs Steel Barrel.

HANDLING & STORAGE: Recommended storage temperature is between +5 C and +40 C. Keep pail tightly closed. Store and handle in a dry, well-ventilated place. Keep away from sources of heat, ignition and direct sunlight in original packaging. Provide grounding and venting in order to prevent static electricity build-up. avoid any contact with Organic Peroxides.

SHELF LIFE: 1 Year For unopened packages at recommended storage conditions.

**Bhagwati Allied Products, Address: K-216, MID C, Waluj, MID C, MIDC, Aurangabad, Maharashtra
431136 Phone: 0240 255 4727**